



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
02.01.2003 Bulletin 2003/01

(51) Int Cl.7: **C08L 91/00**

(21) Application number: **00102201.1**

(22) Date of filing: **10.02.2000**

(54) **Low modulus of elasticity-rubber composition**

Kautschukmischungen mit einem niedrigen Elastizitätsmodul

Compositions de caoutchouc ayant un module d'élasticité faible

(84) Designated Contracting States:
DE FR GB

(30) Priority: **10.02.1999 JP 3292999**

(43) Date of publication of application:
16.08.2000 Bulletin 2000/33

(73) Proprietor: **Sumitomo Rubber Industries, Ltd.**
Kobe-shi, Hyogo 651-0072 (JP)

(72) Inventors:
• **Sakaki, Toshiaki**
Kakogawa-shi, Hyogo 675-0025 (JP)
• **Mizuguchi, Tetsuo**
Nishinomiya-shi, Hyogo 662-0943 (JP)

(74) Representative: **Müller-Boré & Partner**
Patentanwälte
Grafinger Strasse 2
81671 München (DE)

(56) References cited:
EP-A- 0 564 267

- **DATABASE WPI Section Ch, Week 197748**
Derwent Publications Ltd., London, GB; Class
A17, AN 1977-85659Y XP002136219 & JP 52
125562 A (NITTO ELECTRIC IND CO), 21 October
1977 (1977-10-21)
- **DATABASE WPI Section Ch, Week 199619**
Derwent Publications Ltd., London, GB; Class
A17, AN 1996-184974 XP002136220 & JP 08
059925 A (SHOWA ELECTRIC WIRE & CABLE
CO), 5 March 1996 (1996-03-05)

EP 1 028 145 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a low modulus of elasticity-rubber composition prepared by containing a softener in an ethylene-propylene-diene rubber. More particularly, the present invention relates to a low modulus of elasticity-rubber composition comprising an ethylene-propylene-diene rubber and a softener, which shows small compression set even at wide range of temperature, especially at low temperature ranging from -30 to 0°C, excellent flexibility and self-tack, and is useful as a sealant for a telecommunication cable closure.

[0002] An ethylene-propylene-diene rubber (hereinafter abbreviated to EPDM, sometimes) is a terpolymer and is utilized as a rubber composition. With respect to the ethylene-propylene-diene rubber, for example, publicly known techniques described in the following patent publications have been known.

[0003] Japanese Patent Publication (Kokoku) No. 57-24828: This publication discloses a sealing process, which comprises molding a low-temperature vulcanizable composition prepared by adding a peroxide and a redox catalyst to a rubber-like polymer containing, as a main component, an olefin terpolymer comprising ethylene, α -olefin and polyene having a non-conjugated double bond, and optionally mixing an optional component such as filler and softener.

[0004] Japanese Patent Laid-open Publication (Kokai) No. 59-27931: This publication describes a rubber composition comprising an ethylene- α -olefin-polyene copolymer rubber wherein a molar ratio of ethylene to α -olefin having 4 or more carbon atoms is from 80:20 to 97:3, and a diene rubber, and also describes that a softener as one of optional components to be added in the rubber composition can be mixed in the amount of about 100 parts by weight or less based on 100 parts by weight of the rubber composition, however, the strength is lowered when the softener is mixed in the amount larger than the above amount.

[0005] Japanese Patent Publication (Kokoku) No. 60-31875: This publication describes a solvent-free type unsteady sealing material prepared by adding 150 to 1000 parts by weight of a softener and 50 to 1000 parts by weight of silicas and/or short fibers to 100 parts by weight of rubbers containing an ethylene-propylene-diene rubber. By the way, any reference with respect to properties of the ethylene-propylene-diene rubber to be used is not made.

[0006] Japanese Patent Laid-Open Publication (Kokai) No. 60-92380: This publication describes a porous sealing agent comprising ethylene, α -olefin and diolefin as a monomer component, wherein 100 parts of a copolymer having a Mooney viscosity (100°C) of 5 to 30 and 30 to 150 parts by weight of a softener are contained.

[0007] Japanese Patent Laid-Open Publication (Kokai) No. 4-65447: This publication describes a rubber composition for seal parts, which is prepared by adding 20 to 50 parts of a naphthenic or paraffinic process oil as a softener and an antioxidant to an ethylene- α -olefin-diolefin copolymer composition defined by 55 to 70 mol% of an ethylene content, 50 to 100 of a Mooney viscosity (121°C) and 5 to 24 of an iodine value.

[0008] Japanese Patent Laid-Open Publication (Kokai) No. 6-136207: This publication discloses an oil-bleeding chlorinated ethylene- α -olefin copolymer composition comprising 100 parts by weight of a chlorinated ethylene- α -olefin copolymer rubber having a Mooney viscosity at 121°C of 10 to 190 and 10 to 60 parts by weight of a paraffinic process oil, wherein the chlorine content is from 20 to 40% by weight, and also describes that this composition can be used as a polymer for molding a connector, a packing and a housing of an electric circuit.

[0009] As described above, various EPDM rubber compositions containing different components for various purposes have been known and, as a matter of course, required characteristics vary depending on the purposes.

[0010] When using the EPDM rubber composition for sealing in the field of a telecommunication cable closure, it is required that the composition shows small compression set even at wide range of temperature, especially at low temperature ranging from -30 to 0°C, and excellent flexibility. The "closure" used herein means a container for branching and connecting an electric wire and an optical fiber.

[0011] However, it is difficult to provide the previously known EPDM composition for sealing in low temperature range in view of characteristics. In case of a conventional composition, since the compression set at -20°C exceeds 90% and a change in hardness between room temperature and -20°C is very large, there is a fear that the sealability at low temperature such as -20°C is lowered to cause leakage. There is also a problem that compression required for sealing can not be conducted sufficiently as a result of an increase in hardness. In case of almost all of compositions, it is difficult to compress because of poor flexibility and to closely contact with the cable because of poor tack.

[0012] In order to solve the problems described above, the present inventors have studied intensively to improve the EPDM rubber composition. As a result, they have found that a rubber composition, which shows small compression set even at low temperature and excellent flexibility, can be obtained by containing a combination of EPDM having specific properties and a softener having specific properties in a specific ratio. Thus, the present invention has been completed by studying furthermore.

[0013] That is, the present invention provides:

- 1) a low modulus of elasticity-rubber composition comprising an ethylene-propylene-diene rubber and a softener, wherein

EP 1 028 145 B1

(1) the ethylene-propylene-diene rubber has the following properties:

- (a) a Mooney viscosity at 100°C is from 90 to 130,
- (b) a diene is ethyldenenorbornene,
- (c) an iodine value is not more than 20, and
- (d) the amount of ethylene is not more than 55% by weight based on the total amount of ethylene and propylene;

(2) the softener has the following properties:

- (a) a pour point is not higher than -40°C, and
- (b) a SP value is from 6 to 8; and

the softener is contained in the amount of 300 to 700 parts by weight based on 100 parts by weight of the ethylene-propylene-diene rubber, and

2) the low modulus of elasticity-rubber composition according to the term 1), which is vulcanized.

[0014] The low modulus of elasticity-rubber composition of the present invention is suited for use as a seal material of a telecommunication cable closure because it shows flexibility, small compression set even at low temperature range, and excellent tack.

[0015] EPDM used in the rubber composition of the present invention has properties specified by the terms (a), (b), (c) and (d), as described above. With such a composition, the rubber composition shows low elasticity and the JIS A hardness is usually not more than 10. Herein, JIS is abbreviation of Japanese Industrial Standard.

[0016] The Mooney viscosity is an index of the molecular weight of EPDM. The higher the molecular weight, the higher the viscosity becomes. To the contrary, the lower the molecular weight, the lower the viscosity becomes. In the present invention, EPDM having the Mooney viscosity at 100°C within a range from 90 to 130, preferably from 100 to 120, is used. When the molecular weight of EPDM is high, there is a merit of increased strength. On the other hand, it becomes difficult to fill with a large amount of softener and tack of the rubber after vulcanization becomes poor. A high-molecular weight EPDM having the Mooney viscosity of higher than 130 is not preferred for the reasons described above. On the other hand, when the Mooney viscosity is lower than 90, it is possible to fill with a large amount of softener such as oil and the tack is good, however, the vulcanized article is scarcely fit to use because of drastic reduction in strength. EPDM having the Mooney viscosity of 100 to 120 is preferably used.

[0017] The iodine value of EPDM is an index of the amount of the diene component in this rubber, that is, the larger the iodine value, the larger the amount of the diene component. When the iodine value increases, the reactivity increases, thereby facilitate the vulcanization; however, deterioration of the aging resistance and weathering resistance caused by the diene component are liable to occur. In the present invention, EPDM having the iodine value of not more than 20 is selected in view of the aging resistance and weathering resistance. As the diene constituting EPDM, ethyldenenorbornene (ENB) is used; however, there is a merit that the vulcanization rate is increased thereby.

[0018] When the amount of ethylene is represented by a proportion of the amount of ethylene based on the total amount of ethylene and propylene in EPDM, those having a ratio of not more than 55% by weight are selected. When the amount of ethylene is high, there is a merit that the strength of the rubber increases; however, there is a drawback that crystallization occurs at low temperature. Usually, EPDM having the ethylene proportion of 50 to 75% is available, and those having the ethylene proportion of not more than 55%, preferably about 50%, may be selected among them. When the ethylene proportion is not more than 55%, the compression set is noticeably improved even at -20°C or lower as compared with those having the ethylene proportion of about 70%.

[0019] Next, the softener used in the rubber composition according to the present invention is that having a pour point of not more than -40°C, the measurement procedure of which is defined in JIS K2269, and a SP (Solubility Parameter) of 6 to 8. By selecting the one having the pour point of not more than -40°C, this rubber composition can maintain the flexibility and retain good transformability even at a low temperature range.

[0020] When the softener is added in the rubber, a combination of the rubber and softener, which have high affinity each other, is selected. In the present invention, the softener having the SP value of 6 to 8 is selected. As a result, it becomes possible to mix the softener in a large amount such as 300 to 700 parts by weight based on 100 parts by weight of EPDM having the SP value of 7 to 8.

[0021] The softener having the above pour point and SP value can be used in the present invention without being specifically limited, but is selected particularly preferably from paraffinic process oil and oil made of a low molecular weight component of ethylene-propylene. The viscosity of the softener is not specifically limited, but the one having a higher dynamic viscosity, e.g. dynamic viscosity of not less than 50 at 40°C, is preferably used because the tack of

the resulting vulcanized rubber becomes higher.

[0022] Specific examples of the softener include those which are commercially available by the trade name of Diana Process oil PX-32 or PX-90 (IDEMITSU KOSAN CO., LTD.), Stanol LP40 (Esso Petroleum Co., Ltd.) and Lucant HC-10 (MITSUI CHEMICALS, INC.).

5 [0023] In the composition of the present invention, the softener is preferably added in the amount within a range from 300 to 700 parts by weight, and more preferably from 300 to 500 parts by weight, based on 100 parts by weight of EPDM. The specific amount of the softener is appropriately decided according to the purposes of the rubber composition of the present invention so that required characteristics are obtained. For example, when using as a telecommunication cable closure, it is required that the composition has the flexibility and shows small compression set at
10 temperature ranging from low temperature to high temperature, i.e. -30°C to 60°C. In this case, the hardness(JIS K 2220) at normal temperature at 23°C is desirably not less than 50 when the hardness is represented by penetration of a 1/16 inch into the rubber composition, preferably not less than 65, and more preferably not less than 80. When the hardness is smaller than 50, it is too hard and the sealability is lowered. When the upper limit of the penetration is not less than 100, the tack increases excessively and the amount of the softener increases largely, which is not preferred.
15 The specific amount of the softener is selected in such way, but varies depending on the other mixing conditions, as a matter of course.

[0024] The rubber composition of present invention is preferably vulcanized for the purpose of reducing the compression set, thereby enhancing the flexibility. Sulfur or a sulfur-containing compound may be used for vulcanization. Generally, vulcanizate with a peroxide exhibits good compression set specifically at higher temperature range. On the
20 other hand, the vulcanizate with sulfur, wherein molecules are more mobile, is preferably applied at lower temperature range. When using EPDM whose propylene content is comparatively large, there is a fear that the use of the peroxide leads to deterioration of the rubber.

[0025] If necessary, reinforcers, fillers, flame retardants, tackifiers, vulcanization activators, pigments, processing aids, vulcanization accelerators, ultraviolet stabilizers, or antioxidants can be added to the rubber composition of the
25 present invention as exemplified as below (addition amounts are based on 100 parts by weight of the ethylene-propylene-diene rubber).

[0026] As said reinforcer, for example, silica or carbon black can be added in the amount of 0 to 300 parts by weight.

[0027] As said filler, for example, calcium carbonate, clay or magnesium carbonate can be added in the amount of 0 to 300 parts by weight.

30 [0028] As said flame retardant, for example, aluminum hydroxide and antimony trioxide can be added in the amount of 0 to 10 parts by weight.

[0029] As said tackifier, for example, coumarone-indene resin, aliphatic hydrocarbon resin, alicyclic hydrocarbon resin, or low molecular weight component such as liquid polybutene or liquid polyisoprene can be added in the amount of 0 to 200 parts by weight. The low molecular weight component having the SP value of 6 to 8 and the pour point of
35 not more than -40°C, such as liquid polybutene or liquid polyisoprene, can be used as softener in the present invention.

[0030] As said vulcanization activator, for example, zinc oxide or stearic acid can be used in the total amount of 3 to 200 parts by weight.

[0031] As said pigment, for example, any of organic or inorganic pigment can be used, and examples thereof include lithopone, titanium oxide or carbon black.

40 [0032] As said processing aid, for example, stearic acid or fatty ester can be used in the amount of 0 to 50 parts by weight. As said vulcanization accelerator, for example, thiazole, thiuram, dithiocarbamate or sulfenamide vulcanization accelerator can be used in the amount of 2 to 20 parts by weight.

[0033] The rubber composition of the present invention is produced by mixing EPDM with the softener and kneading the mixture. The softener is added in the amount of 300 to 700 parts by weight, as described above, however, the other
45 additives are not sufficiently dispersed in the rubber when this amount of the softener is added in EPDM in one dose. There is also a problem that the softener is hardly mixed with EPDM uniformly and it requires a very long time to mix then completely. To avoid the problem, all the additives other than the softener and about 0 to 100 parts by weight of the softener should be sufficiently dispersed. Thereafter, when the remaining softener is introduced in one or several doses, a uniform rubber composition can be efficiently obtained. A conventional kneader can be used in the kneading
50 operation.

[0034] The following Examples and Comparative Examples further illustrate the present invention in detail. The quality of the rubber composition was evaluated by the following procedure.

[Test procedure]

55

[0035] Compression set: It was measured in accordance with JIS K6262 under the condition that the compressing time was 24 hours and the temperature was -20°C. The thickness was measured immediately after removing of compression, since the compression set would be reduced with the raise of the temperature.

EP 1 028 145 B1

[0036] The compression set at -20°C is preferably not more than 40 % so that the rubber composition can be used as a sealant even at low temperature.

[0037] Penetration: It was measured by using a cone A in 1/1 size according to the consistency measuring procedure defined in JIS K2220. The measuring temperature was adjusted to 23°C.

5 [0038] Appearance: Bleed of the softener was evaluated by visually observing the subject or feeling it with tip of fingers according to the following criteria.

○: no feel of bleed by touch

Δ: bleed is visually observed, but feel slight bleed by touch

10 ×: bleed is visually observed

[0039] Tack: It was evaluated by feeling the subject with tip of fingers according the following three-grade criteria:

○: inevitable tack

15 Δ: slightly poor tack

×: poor tack

[0040] Strength: It was evaluated by making a cut in the subject using a knife, pulling it with hands, and observing whether the cut is enlarged or not according the following three-grade criteria.

20 ○: cut hardly propagates

Δ: requires careful handling because cut propagates when pulling largely

×: not suited for practical use because of drastic propagation of cut

25 Examples 1 to 3

[0041] 100 Parts by weight of Esprene 532 as EPDM (content of ethylene based on the total amount 100 of ethylene and propylene: 50% by weight, Mooney viscosity at 100°C: 110, iodine value: 12 g/100 g, diene component: ENB) manufactured by Sumitomo Chemical Co., Ltd. and additives shown in Table 1 were kneaded using a kneader.

30

[Table 1]

Components	Parts by weight
Zinc oxide	150
Stearic acid	4.5
CB (GPF)	5
Vulcanization accelerator M	1
Vulcanization accelerator TET	0.5
Vulcanization accelerator BZ	0.5
Sulfur	1
Total	262.5

35

40

[0042] Parts are by weight based on 100 parts by weight of EPDM

45 CB (GPF): carbon black (grade: N660)

M: 2-mercapto benzothiazole

TET: tetraethylthiuram disulfide

BZ: zinc dibutyl dithiocarbamate

50 [0043] After kneading, EPDM was crushed into powder. First, 100 parts by weight of a softener (paraffinic process oil manufactured by IDEMITSU KOSAN CO., LTD. by the trade name of Diana PX-90, pour point: -45°C, dynamic viscosity: 110 cSt at 40°C, SP value: 7.1) was introduced into the kneaded powder. At this stage, they were kneaded until a sufficient torque is applied during the kneading. The dispersibility of the respective components in the resulting rubber composition was very good. While kneading this rubber composition, the remaining softener was further introduced in three doses. The total amount of the softener was adjusted to three levels, for example, 450, 350 and 650 parts by weight based on 100 parts by weight of EPDM, which were taken as Examples 1, 2 and 3, respectively. After the completion of the kneading, the rubber composition was vulcanized to form a predetermined shape, which was subjected to tests. The results are also shown in Table 2.

55

EP 1 028 145 B1

Comparative Examples 1 and 2

5 [0044] In the same manner as in the above Examples, except that the amount of the softener was changed to 250 parts by weight (Comparative Example 1) or 800 parts by weight (Comparative Example 2) as shown in Table 2, the rubber, softener, and other ingredients were kneaded to prepare a composition, respectively. The results of the tests are shown in Table 2.

Comparative Example 3

10 [0045] In the same manner as in the above Examples, except that 100 parts by weight of Esperene 532 was used as EPDM and 650 parts by weight of Diana PW-380 (paraffinic process oil manufactured by IDEMITSU KOSAN CO., LTD.) was used as the softener as shown in Table 2, a rubber composition was prepared. The results of the tests are shown in Table 2.

15 Comparative Example 4

[0046] In the same manner as in the above Examples, except that 200 parts by weight (containing 100 parts by weight of extension oil) of Esperene 670F (manufactured by Sumitomo Chemical Co., Ltd.) was used as EPDM and 350 parts by weight of Diana PW-380 was used as the softener as shown in Table 2, a rubber composition was prepared.
20 The results of the tests are shown in Table 2.

Comparative Example 5

25 [0047] In the same manner as in the above Examples, except that 200 parts by weight (containing 100 parts by weight of extension oil) of Esperene 670F was used as EPDM and 350 parts by weight of Diana PX-32 (paraffinic process oil manufactured by IDEMITSU KOSAN CO., LTD.) was used as the softener as shown in Table 2, a rubber composition was prepared. The results of the tests are shown in Table 2.

Comparative Example 6

30 [0048] In the same manner as in the above Examples, except that 100 parts by weight of Esperene 505A (manufactured by Sumitomo Chemical Co., Ltd.) was used as EPDM and 350 parts by weight of Diana PW-380 was used as the softener as shown in Table 2, a rubber composition was prepared. The results of the tests are shown in Table 2.

35

40

45

50

55

[Table 2]

	Example 1	Example 2	Example 3	Comp. Example 1	Comp. Example 2
EPDM	Esprene 532	Esprene 532	Esprene 532	Esprene 532	Esprene 532
Ethylene content (%)	50	50	50	50	50
Mooney viscosity ML(1+4)(100°C)	110	110	110	110	110
Iodine value (g/1000 g)	12	12	12	12	12
Diene component	ENB	ENB	ENB	ENB	ENB
Softening agent	Diana PX-90	Diana PX-90	Diana PX-90	Diana PX-90	Diana PX-90
Parts by weight	450	350	650	250	800
Pour point (°C)	-45	-45	-45	-45	-45
SP value	7.1	7.1	7.1	7.1	7.1
Penetration	95	64	145	38	173
Tack	○	○	○	○	○
Appearance	○	○	○	○	○-Δ
Strength	○	○	Δ	○	×
Compression set (-20°C)	20	20	24	22	24

ENB: ethyldenenorbornene, *: assumed value

[Table 2] (continued)

	Comp. Example 3	Comp. Example 4	Comp. Example 5	Comp. Example 6
EPDM	Esprene 532	Esprene 670F	Esprene 670F	Esprene 505A
Ethylene content (%)	50	70	70	55
Mooney viscosity ML(1+4)(100°C)	110	230*	230*	45
Iodine value (g/1000 g)	12	12	12	24
Diene component	ENB	ENB	ENB	ENB
Softening agent	Diana PW-380	Diana PW-380	Diana PX-32	Diana PW-380
Parts by weight	650	350	350	350
Pour point (°C)	-15	-15	-45	-15
SP value	6.9	6.9	7.5	6.9
Penetration	132	41	45	41
Tack	○	X	X	○
Appearance	○	○	○	○
Strength	○	○	○	X
Compression set (-20°C)	78	95	92	82

ENB: ethylenenorbornene, *: assumed value

[0049] As is apparent from the results of the evaluation shown in Table 2, the rubber compositions (Examples 1, 2 and 3), which are prepared by using 100 parts by weight of EPDM having an ethylene content of not more than 55%,

EP 1 028 145 B1

a Mooney viscosity at 100°C of 90 to 130 and an iodine value of not more than 20 and 300 to 700 parts by weight of a softener having a pour point of not higher than -40°C and a SP value of 6 to 8, are flexible and show small compression set even at low temperature and, therefore, they have preferred characteristics for the sealing material.

5 [0050] On the other hand, when the conditions specified in the present invention are not satisfied, the rubber composition having satisfactory quality was not obtained as shown in the respective Comparative Examples.

Claims

10 1. A low modulus of elasticity-rubber composition comprising an ethylene-propylene-diene rubber and a softener, wherein

(1) the ethylene-propylene-diene rubber has the following properties:

- 15 (a) a Mooney viscosity at 100°C is from 90 to 130,
(b) a diene is ethylidenenorbornene,
(c) an iodine value is not more than 20, and
(d) the amount of ethylene is not more than 55% based on the total amount of ethylene and propylene;

20 (2) the softener has the following properties:

- (a) a pour point is not higher than -40°C, and
(b) a SP value is from 6 to 8; and

25 the softener is contained in the amount of 300 to 700 parts by weight based on 100 parts by weight of the ethylene-propylene-diene rubber.

2. The low modulus of elasticity-rubber composition according to claim 1, which is vulcanized.

30 3. The low modulus of elasticity-rubber composition according to claim 1 or 2, wherein the Mooney viscosity of ethylene-propylene-diene rubber is from 100 to 120 at 100°C.

35 4. The low modulus of elasticity-rubber composition according to one or more of claims 1 to 3, wherein the softener is one or more member selected from the group consisting of a paraffinic process oil and an oil made of a low-molecular-weight component ethylene-propylene.

40 5. The low modulus of elasticity-rubber composition according to one or more of claims 1 to 4, wherein the softener is contained in the amount of 300 to 500 parts by weight based on 100 parts by weight of the ethylene-propylene-diene rubber.

6. The low modulus of elasticity-rubber composition according to one or more of claims 1 to 5, wherein a hardness of said composition is not less than 50 when the hardness is represented by penetration of a 1/1 con into the composition.

45 7. The low modulus of elasticity-rubber composition according to one or more of claims 1 to 6, which is for as a sealant of a telecommunication cable closure.

Patentansprüche

50 1. Gummizusammensetzung mit niedrigem Elastizitätsmodul, umfassend ein Ethylen-Propylen-Dien-Gummi und einen Weichmacher, wobei

(1) der Ethylen-Propylen-Dien-Gummi die folgenden Eigenschaften aufweist:

- 55 (a) eine Mooney-Viskosität bei 100°C ist von 90 bis 130,
(b) ein Dien ist Ethylidennorbornen,
(c) ein Iodwert ist nicht mehr als 20 und

EP 1 028 145 B1

(d) die Ethylenmenge ist nicht mehr als 55% basierend auf der Ethylen- und Propylengesamtmenge;

(2) der Weichmacher die folgenden Eigenschaften aufweist:

- 5 (a) ein Fließpunkt ist nicht höher als -40°C und
(b) ein SP-Wert ist von 6 bis 8; und

der Weichmacher ist in einer Menge von 300 bis 700 Gewichtsteilen basierend auf 100 Gewichtsteilen des Ethylen-Propylen-Dien-Gummis enthalten.

10

2. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach Anspruch 1, die vulkanisiert ist.

3. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach Anspruch 1 oder 2, wobei die Mooney-Viskosität von Ethylen-Propylen-Dien-Gummi von 100 bis 120 bei 100°C ist.

15

4. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach einem oder mehreren der Ansprüche 1 bis 3, wobei der Weichmacher ein oder mehrere Mitglieder ist, ausgewählt aus der Gruppe, bestehend aus einem Paraffin-Verfahrensöl und einem Öl, welches aus einem Niedermolekulargewichtskomponenten Ethylen-Propylen hergestellt ist.

20

5. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach einem oder mehreren der Ansprüche 1 bis 4, wobei der Weichmacher in der Menge von 300 bis 500 Gewichtsteilen auf 100 Gewichtsteile des Ethylen-Propylen-Dien-Gummis enthalten ist.

25

6. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach einem oder mehreren der Ansprüche 1 bis 5, wobei eine Härte der Zusammensetzung nicht weniger als 50 ist, wenn die Härte durch die Eindringtiefe eines 1/1 Korns in die Zusammensetzung dargestellt ist.

30

7. Gummizusammensetzung mit niedrigem Elastizitätsmodul nach einem oder mehreren der Ansprüche 1 bis 6, die als Dichtmittel eines Fernmeldekabelverschlusses dient.

Revendications

35 1. Composition de caoutchouc à bas module d'élasticité, comprenant un caoutchouc éthylène-propylène-diène et un agent ramollissant, dans laquelle

(1) le caoutchouc éthylène-propylène-diène a les propriétés suivantes :

40

(a) une viscosité Mooney à 100°C comprise dans l'intervalle de 90 à 130,

(b) le diène est l'éthylidène-norbornène,

(c) un indice d'iode non supérieur à 20, et

(d) une quantité d'éthylène non supérieure à 55 % sur la base de la quantité totale d'éthylène et de propylène ;

45

(2) l'agent ramollissant a les propriétés suivantes :

(a) un point d'écoulement non supérieur à -40°C, et

(b) une valeur SP de 6 à 8 ; et

50

l'agent ramollissant est présent en une quantité de 300 à 700 parties en poids sur la base de 100 parties en poids du caoutchouc éthylène-propylène-diène.

2. Composition de caoutchouc à bas module d'élasticité suivant la revendication 1, qui est vulcanisée.

55

3. Composition de caoutchouc à bas module d'élasticité suivant la revendication 1 ou 2, dans laquelle la viscosité Mooney du caoutchouc éthylène-propylène-diène est comprise dans l'intervalle de 100 à 120 à 100°C.

EP 1 028 145 B1

4. Composition de caoutchouc à bas module d'élasticité suivant une ou plusieurs des revendications 1 à 3, dans laquelle l'agent ramollissant consiste en un ou plusieurs membres choisis dans le groupe consistant en une huile plastifiante paraffinique et une huile formée d'un constituant éthylène-propylène de bas poids moléculaire.
- 5 5. Composition de caoutchouc à bas module d'élasticité suivant une ou plusieurs des revendications 1 à 4, dans laquelle l'agent ramollissant est présent en une quantité de 300 à 500 parties en poids sur la base de 100 parties en poids du caoutchouc éthylène-propylène-diène.
- 10 6. Composition de caoutchouc à bas module d'élasticité suivant une ou plusieurs des revendications 1 à 5, dans laquelle la dureté de ladite composition est non inférieure à 50 lorsque la dureté est représentée par la pénétration d'un coin 1/1 dans la composition.
- 15 7. Composition de caoutchouc à bas module d'élasticité suivant une ou plusieurs des revendications 1 à 6, qui est destinée à jouer le rôle d'agent d'étanchéité d'une enveloppe de fermeture de câble de télécommunication.

15

20

25

30

35

40

45

50

55